SATURATED POLYESTER POLYOLS FOR POLYURETHANE SYSTEMS FOR FOOTWEAR INDUSTRY

Elapol is a worldwide brand of saturated polyester polyols for polyurethane systems used in footwear, flexible and rigid PU foams, cast elastomers and TPU, polyurethane adhesives, and polyurethane coatings.

TECHNICAL PRODUCT BROCHURE

















100% ELACHEM
BUILT ON CHEMISTRY.
INSPIRED BY PEOPLE.





WE ARE ELACHEM PEOPLE.

Founded in Vigevano, Italy, in 2001, Elachem® S.p.A. is a wholly Italian-owned company that has established itself as an international leader in the production of saturated polyesters, polyurethane systems, and high-performance materials.

With an annual production capacity of 95,000 tonnes of saturated polyesters and 50,000 tonnes of polyurethane systems, the company supplies partners worldwide with innovative, tailor-made solutions.

The acquisition of Epaflex® Polyurethanes in 2008 further expanded its portfolio, adding Thermoplastic Polyurethanes (TPU), elastomers, and other advanced technologies.

At the heart of Elachem®'s innovation are its state-of-the-art laboratories, which oversee the entire development process, from product design to final testing.

FIND WHAT SPEAKS TO YOU.

Explore the four product areas
at the heart of our expertise.

SATURATED POLYESTER

Elapol® is our worldwide brand of saturated polyester polyols for flexible and rigid PU foams, casting elastomers and TPU, polyurethane adhesives and coatings, and polyurethane systems for footwear.

POLYURETHANE SYSTEMS

Our polyurethane systems bring technical precision with a dash of Italian soul.

Our expertise is focused across three key areas: Casual & Sport, Safety, and Fashion, each developed to meet specific performance and design needs.

TPU AND CASE

Epaflex has been actively involved for more than 30 years in manufacturing and supply of polyurethane (PU) systems and thermoplastic polyurethane granules (TPU) in a wide range of industrial sectors. The range of products offered is constantly evolving, thanks to the commitment and resources invested in research and application development.

PRIVATE LABEL

Discover our range dedicated to manufacturers: exclusive brand formulations, produced by Epaflex Polyurethanes S.p.A. and Elachem® S.p.A. to the highest quality standards.

Discover the full range of products on elachem.com

WE SMILE OFTEN.



WE MEAN BUSINESS.

OUR RANGE OF SATURATED POLYESTER

Elachem S.p.A. offers a broad range of aliphatic and aromatic polyester polyols.

The Saturated Polyester Polyols Division focuses its activities on production and manufacturing processes for the PU industry, in compliance with the highest EHS standards.

Elachem's technical teams provide tailor-made solutions to meet your technological requirements.

Elapol is a worldwide brand of saturated polyester polyols for polyurethane systems used in footwear, flexible and rigid PU foams, cast elastomers and TPU, polyurethane adhesives, and polyurethane coatings.

SATURATED POLYESTER POLYOLS FOR POLYURETHANE SYSTEMS FOR FOOTWEAR INDUSTRY

Branched and linear Saturated Polyesters manufactured with synthetic acids and glycols. Excellent mechanical properties and low density. Branched and linear Saturated Polyesters manufactured with dicarboxylic acids and glycols. Used in polyols for the production of sandals with low moulding density. Being slightly branched, extraction time is reduced.

ELAPOL	ACIDS/ ANHYDRIDES	MAIN GLYCOLS	STRUCTURE	APPEARANCE	OH NUMBER mg KOH/g		ACID NUMBER mg KOH/g	BROOKFIELD VISCOSITY mPa·s	WATER CONTENT %	HAZEN COLOUR	FIELD OF USE
7025 B	**Aliphatic**	**DEG**	Branched	**Liquid**	**59 - 63**		**0,9 - 1,5**	**8800 - 9800 (35°C)**	**≤ 0,1**	**≤ 150**	Mainly used for prepolymers and polyols for the production of women's and men's shoe soles with good performance in temperate climates
7020 B	**Aliphatic**	**DEG**	Branched	**Liquid**	**64 - 68**		**≤ 0,5**	**4000 - 4600 (35°C)**	**≤ 0,1**	**≤ 150**	

ELAPOL	ACIDS/ ANHYDRIDES	MAIN GLYCOLS	STRUCTURE	APPEARANCE	OH NUMBER mg KOH/g		ACID NUMBER mg KOH/g	BROOKFIELD VISCOSITY mPa·s	WATER CONTENT %	HAZEN COLOUR	FIELD OF USE
2030 A	**Aliphatic**	**MEG, DEG**	Linear	**Clear after heating**	**44 - 48**		**≤ 0,5**	**5700 - 6300 (35°C)**	**≤ 0,05**	**≤ 150**	Can be used for the production of prepolymers and polyols. Good flexing resistance and physical properties. Used in the production of men's and women's footwear in temperate climates.
2130 B	**Aliphatic**	**MEG, DEG**	Linear	**Clear after heating**	**38 - 42**		**≤ 0,5**	**8300 - 9300 (35°C)**	**≤ 0,1**	**≤ 150**	
2020 B	**Aliphatic**	**MEG, DEG**	Linear	**Clear after heating**	**54 - 58**		**≤ 0,7**	**4200 - 4700 (35°C)**	**≤ 0,1**	**≤ 150**	
2010 B	**Aliphatic**	**MEG, DEG**	Linear	**Waxy**	**108 - 116**		**≤ 0,6**	**1150 - 1250 (35°C)**	**≤ 0,1**	**≤ 100**	

ELAPOL	ACIDS/ ANHYDRIDES	MAIN GLYCOLS	STRUCTURE	APPEARANCE	OH NUMBER mg KOH/g		ACID NUMBER mg KOH/g	BROOKFIELD VISCOSITY mPa·s	WATER CONTENT %	HAZEN COLOUR	FIELD OF USE
1120 B	**Dicarboxylic**	**MEG, DEG**	Linear	**Clear**	**54 - 58**		**≤ 0,5**	**650 - 750 (75°C)**	**≤ 0,03**	**≤ 12 (Gardner)**	Used in polyols for the production of sandals with low moulding density. Being slightly branched, extraction time is reduced
1020 GL	**Dicarboxylic**	**MEG**	Branched	**Liquid**	**59 - 64**		**≤ 0,5**	**9000 - 11000 (35°C)**	**≤ 0,1**	**≤ 18 (Gardner)**	

elachem.com

Worldwide exporter of Saturated Polyester,
Polyurethane Systems, TPU and CASE

OPERATING OFFICE

C.so Torino, 129 27029
Vigevano (PV), Italy

tel. +39 0381 327112

LET'S TALK

Commercial Director
Polyester Division

mattia.giannoni@elachem.com

OUR COMMITMENT

© 2026 Elachem S.p.A. All rights reserved. **ART DIRECTION AND GRAPHIC DESIGN**: vitamineD
PHOTOGRAPHY: portraits by Claudio Bonoldi Studio, additional images sourced from stock libraries.